2300 - Easy Clear

Product Description

2300 is an easy to apply high solid clearcoat with its ultimate flow and durable gloss.It is mainly suggested for fast-hand painters.

Suitable Substrates

- GenRock basecoat

Product Application



100% Clear	50% Hardener	5-10% Thinner
2300	H700 SLOW	S721 SLOW
	H600 NORMAL	S711 NORMAL
	H700 SLOW	S719 FAST



15-16s / DIN 4 mm / 20°C



HVLP 1.3 – 1.4 mm(2 coats)
0.7 bar atomization pressure
1 medium + full coat
50 µm



Flash off 2-3 minutes between coats
10 minutes before low bake
Low Bake 20 min at 60°C panel temperature



Short Wave 10-15 min
Panel > 80cm from IR unit

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

	Wear suitable protection

Product Characteristics

Specific Gravity:	0.985 kg/cm^3
Flash Point:	25^{o}C (77^{o}F)
Solid Content:	46.2 % by weight
Coverage:	8 - 9 m^2/l at 50-micron dry film thickness (theoretical)
SDS:	Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.