



800TS - 1K Tintable Sealer

Product Description:

800TS is a tinted 1Klaknik car polish with a velvety smooth finish. 800TS is part of the General mixing system, so it is fully supplied with General basecoat shades. 800TS does not cause problems with delicate application.

800TS dries quickly, helps avoid scratching characteristic by half and provides color uniformity for the brown basecoat.


Surface preparation:

- The old paint was thoroughly sanded and the surfaces were well primed and prepared.

Suitable substrates:

- Existing finishes except TPA
- 1K or 2K "GENERAL" primers
- OEM or EDP primer, sanded
- "GENERAL" polyester putties
- Bare metal substrates must be pre-primed with 9700 wash primer

Product Application



Thinners 100% "General" (as a clear sealer)

Mix one (1) part 800TS Sealer with one (1) to (2) parts Basecoat Tints (depending on color coverage). Thin 75% at appropriate speed with General Reducer.

Mix one (1) part 800TS with one (1) part General Reducer to use as a clear sealer.



18-19 sek. / DIN 4 mm / 20°C (68°F)



Compliant 1.4–1.5 mm
2.0–2.5 bar inlet pressure
HVLP 1.4–1.5 mm; 0.7 bar at air cap
8–12 microns per coat

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



800TS - 1K Tintable Sealer



5 min. between layers.



Wait until the polish is completely matte before applying the top coat.

Product characteristics

Specific Gravity 1.09 kg/cm³

Flash Point 27°C

Solid Content 42% by weight

Coverage 8 - 10 m²/l at a dry layer thickness of 25 microns (theoretically)

SDS: Please read the safety data sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.